

Supplied by:

AMBER COMPOSITES
 Amber Composites Limited, 94 Station Road,
 Langley Mill, Nottingham NG16 4BP
 Telephone: +44 (0) 1773 530899 Fax: +44 (0) 1773 768687
 E-mail: sales@ambercomposites.co.uk
 Web: www.ambercomposites.co.uk

RAKU-TOOL[®] MB-0720

Board Material

Polyurethane Board for Modeling

PC - Rev.-Status: 01- 2006/01/06

Page 1 of 2

Key Properties

- Fine surface structure
- Low coefficient of thermal expansion
- Good dimensional stability
- Good compressive and flexural strength

Applications

- Master models
- Cubing models
- Patterns

Mechanical Properties

| | | | MB-0720 |
|----------------------------------|-----------|----------------------------------|---------|
| Color | visual | | Brown |
| Density | ISO 1183 | g/cm ³ | 0.72 |
| Shore hardness D | ISO 868 | | 60 – 65 |
| Coefficient of thermal expansion | ISO 11359 | 10 ⁻⁶ K ⁻¹ | 50 – 55 |
| Deflection temperature, HDT | ISO 75 | °C | 75 – 80 |
| Compressive strength | ISO 604 | MPa | 20 – 25 |
| Flexural strength | ISO 178 | MPa | 25 – 30 |

Processing

The product should have a temperature of 20°C – 25°C during processing.

PackagingRAKU-TOOL[®] MB-0720
 1500 x 500 x 25 mm
 1500 x 500 x 50 mm
 1500 x 500 x 75 mm
 1500 x 500 x 100 mm
 1500 x 500 x 150 mm
 1500 x 500 x 200 mm
Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL[®] MB-0720

Board Material

Polyurethane Board for Modeling

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
